

Models Cleaning Procedure using NaOH (Sodium Hydroxide)

An optional treatment of finished models, using inexpensive, commercially available Sodium Hydroxide diluted in water.

Applications & Benefits

- Slightly improves surface finish, eliminates small amount of residue left on surface.
- Improves transparency to some extent.
- Makes separation of support model easier, specially for tight tolerance or moving parts.
- For very complicated parts with longer support removal - greatly decreases time for WaterJet support removal.

Recommendations on when to use

- For models requiring painting or silicon moulds.
- Any model where surface touch/feeling is key factor.

How does it work?

- The product to buy is pure Sodium Hydroxide (known also as caustic soda, or NaOH). It is a chemical commonly used in commercially available products such as cleaners or to unblock drains.
- Available in pure form any hardware store or DIY store.
- It is recommended to replace the solution once a week so that cleaning is optimal.
- Please note, all parts must still undergo WaterJet support removal before this cleaning.
- Fine sandpaper can still be used for a glossier finish.
- All handling of Sodium Hydroxide should be done according to local safety conditions

Any side effects?

- This soaking should not surpass 2 hours otherwise there is a risk of deformation
- For the large majority of models, there will be no effect on mechanical properties.
- For models with thin walls <1 mm in z direction (less so in x and y), there may be slight deformation so these models should be soaked for a shorter time.

Model Cleaning Procedure

This cleaning procedure is intended as a surface preparation procedure, especially desirable, before sand blasting or painting.

This procedure requires the use of eyes protective goggles and hand latex gloves.

Sodium hydroxide solution is an alkaline (basic) solution that should not come in contact with eyes and skin.

In case of accidental eyes or skin direct contact with the sodium hydroxide solution, immediately thoroughly clean the contacted area with running tap water.

1. Remove the support material and clean the model as thoroughly as possible. The use of Objet's Waterjet is strongly recommended.
2. Immerse the model into a 2% Sodium Hydroxide for approximately 1-2 Hrs.
3. Immediately rinse the model using running tap water. A second water jet cleaning at this moment is most recommended.
4. Wipe the water from the model using wiping paper and wait till the MODEL is completely dry. Otherwise, for faster drying, it is recommended to immerse the model in Isopropyl alcohol for a few seconds and let it to dry at room temperature for approximately half an hour.

Surface preparation Solution

For a 1 liter solution:

1. Place 20gr Sodium hydroxide directly into a ~1.5 liter plastic (Polyethylene, Polypropylene, etc) or glass container.
2. Add water to complete 1000 gr (980 grams water +20 gr sodium hydroxide).
3. Gently stir till complete sodium hydroxide dissolution (about 5 minutes).
4. Let the solution cool down to room temperature (The dissolution process of sodium hydroxide produces heat).

The solution is ready and can be used to clean several models, depending on the models size.

Disclaimer

Objet Geometries Ltd. is not responsible for misuse of our products or their use in conjunction with unsafe or improperly maintained equipment or for uses other than intended as specified in this application note.

**Objet Geometries Ltd.
Headquarters**
2 Holzman St., Science
Park
P.O.Box 2496,
Rehovot 76124, Israel
Tel: +972-8-931-4314
Fax: +972-8-931-4315

**Objet Geometries Ltd.
Europe**
Leuvensesteenweg 388
1932 Sint-Stevens-
Woluwe
Belgium
Tel: +32-2-717-6502
Fax: +32-2-717-6500

**Objet Geometries Inc.
North America**
5 Fortune Drive
Billerica,
MA 01821
USA
Tel: 1-877-489-9449
Fax: 1-866-676-1533

**Objet Geometries
AP Limited**
13 Floor, Unit 52A,
HITEC,
1 Trademart Drive
Kowloon Bay
Hong Kong
Tel: +852-2174-0111
Fax: +852-2174-0555

©2007 Objet Geometries, Ltd. Objet™, Objet Geometries™, PolyJet™, Eden250™, Eden260™, Eden330™, Eden350™, Eden350V™, Eden500V™, Eden™, SHR™, PolyLog™, QuadraTempo™, Objet Quadra™, FullCure® and Objet Studio™ are trademarks of Objet Geometries Ltd. and may be registered in certain jurisdictions. All other trademarks belong to their respective owners.